

REZSTONE

Epoxy Floor Systems

SPECIFICATIONS

9230 TWO-COAT EPOXY FLOOR COATING SYSTEM

Description:

Rez-Stone 9230 is a two-coat epoxy floor system designed for hi-build epoxy protection over new or like new concrete substrates. Rez-Stone 9230 provides high gloss, flat-line finish, and excellent wear resistance on light-to-heavy industrial floor applications. Rez-Stone 9230 incorporates two coats of 100% solids epoxy for an economical, long-lasting, 30 mil floor system.

Advantages:

- ✓ Economical
- ✓ Easy two-coat application
- ✓ Excellent light reflectivity
- ✓ Solvent free
- ✓ No VOC's

Limitations:

- ✓ Substrate minimum temperature 50°F
- ✓ New concrete must be at least 28 days old
- ✓ Substrate must be clean and sound

Coverage:

Actual coverage may vary due to the existing surface conditions. The following can be used as a guide for new or like new concrete conditions.

Prime Coat	175 – 225 Square Feet per Gallon (8 mils)	Rez-Stone 5017
Topcoat	75 Square Feet per Gallon (22 mils)	Rez-Stone 5058

Surface Preparation:

Concrete surfaces must be clean and sound. Remove all dirt, laitance, grease, curing compounds, and other bond-inhibiting contaminants by shot blasting, scarification, or other approved mechanical methods. Due to the relatively thin film thickness of the system, brush blasting is recommended with a S-280 shot or smaller to prevent blast marks from telegraphing through the coating. Treated surfaces must be magnetically broomed to remove all steel shot, and vacuumed to remove all dust and dirt before applying any coatings.

Application:

After proper surface preparation, the concrete surface will be primed using a straight tight squeegee coat of Rez-Stone 5017 epoxy (approximately 8 mil D.F.T.). After curing of the primer, all cracks and holes may be patched with a putty knife or trowel using Rez-Stone 2610 epoxy crack repair kit. After patching, a topcoat of Rez-Stone 5058 may be applied with a notched squeegee at the rate of 75 square feet per gallon (approximately 22 mils D.F.T.) and lightly back-rolled for a smooth flat-line finish. Do not allow more than 24 hours between epoxy coatings. If more time passes over, cured surface must be lightly sanded or screened before applying additional coatings to prevent inner coat adhesion problems.

Safety Precautions:

Prolonged or repeated exposure to epoxy materials may cause eye or skin irritation. If contact occurs, wash affected area with soap and water immediately. If discomfort continues seek medical attention. Always wear suitable protective clothing and use proper safety devices. See respective MSDS for complete details.

Clean-Up:

All tools and equipment should be cleaned before material gels. Use Rez-Stone 1201 epoxy reducer.



Warranties: Hoover & Wells, Inc. warrants the quality of its Rez-Stone products, and takes responsibility only for furnishing specifications and recommendations for their proper installation. Hoover & Wells, Inc. hereby disclaims all other warranties expressed or implied, and any implied warranties of merchantability or fitness for a particular purpose. Hoover & Wells, Inc. shall have no liability to the Purchaser for any property damage, bodily injury, death or other loss arising out of possession or use of Rez-Stone products. Hoover & Wells, Inc. shall not be responsible for any claim resulting from failure to use its product other than the manner outlined with the instructions provided for use of the products. Under no circumstances shall Hoover & Wells, Inc. be liable for any damages or otherwise in excess of the purchase price. Any claim for breach of warranty shall be given to Hoover & Wells, Inc. in writing with 90 days of delivery or the claim shall be deemed waived. All information here is provided in good faith only as an aid to the Purchaser. Thus, the Seller does not guarantee the accuracy of the information and assume no liability for reliance thereof. Rez-Stone® is a registered trademark of Hoover & Wells, Inc.

9230 TYPICAL PROPERTIES AND SPECIFICATIONS OF CURED SYSTEM

Tensile Strength ASTM D-638	2,400 psi
Compressive Strength ASTM C-579	9,200 psi
Flexural Strength ASTM D-790	4,300 psi
Tensile Elongation	10%
Bond Strength	Greater 300 psi (concrete failure)
Flammability ASTM D-635	Self-extinguishing
Electrical Conductivity	Non conductive
Water Absorption % ASTM D-570	0.10
Color	Available in clear and all standard colors

Warranties: Hoover & Wells, Inc. warrants the quality of its Rez-Stone products, and takes responsibility only for furnishing specifications and recommendations for their proper installation. Hoover & Wells, Inc. hereby disclaims all other warranties expressed or implied, and any implied warranties of merchantability or fitness for a particular purpose. Hoover & Wells, Inc. shall have no liability to the Purchaser for any property damage, bodily injury, death or other loss arising out of possession or use of Rez-Stone products. Hoover & Wells, Inc. shall not be responsible for any claim resulting from failure to use its product other than the manner outlined with the instructions provided for use of the products. Under no circumstances shall Hoover & Wells, Inc. be liable for any damages or otherwise in excess of the purchase price. Any claim for breach of warranty shall be given to Hoover & Wells, Inc. in writing with 90 days of delivery or the claim shall be deemed waived. All information here is provided in good faith only as an aid to the Purchaser. Thus, the Seller does not guarantee the accuracy of the information and assume no liability for reliance thereof. Rez-Stone® is a registered trademark of Hoover & Wells, Inc.

